

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Inorganic Acids	Hydrochloric acid	HCl (7647-01-0)	2%	P	-
			1%	M	-
	Nitric acid	HNO <sub>3</sub> (7697-37-2)	5%	P	-
			1%	Ex	-
Phosphoric acid (orthophosphoric acid)	H <sub>3</sub> PO <sub>4</sub> (7664-38-2)	5%	P	-	
		1%	Ex	-	
Sulfuric acid	H <sub>2</sub> SO <sub>4</sub> (7664-93-9)	5%	P	-	
		2%	G	-	
		1%	Ex	-	
Organic Acids	Acetic acid (ethanoic acid)	CH <sub>3</sub> COOH (64-19-7)	2%	M	-
	Lactic acid	C <sub>3</sub> H <sub>5</sub> O <sub>3</sub> (64-19-7)	5%	P	-
Alcohols	n-Butanol (butyl alcohol)	C <sub>4</sub> H <sub>9</sub> OH (71-36-3)	-	Ex	-
	Ethanol (ethyl alcohol)	CH <sub>3</sub> CH <sub>2</sub> OH (64-17-5)	-	Ex	-
	Ethylene glycol (ethan-1,2-diol, monoethylene glycol, MEG)	(CH <sub>2</sub> OH) <sub>2</sub> (107-21-1)	-	Ex	-
	Glycerol (glycerine, propane-1,2,3-triol)	HOCH <sub>2</sub> CH(OH)CH <sub>2</sub> OH (56-81-5)	-	Ex	-
	Higher alcohols	C <sub>n</sub> H <sub>(2n+1)</sub> OH where n > 2	-	Ex	-
	Methanol (methyl alcohol)	CH <sub>3</sub> OH (67-56-1)	-	G	-
	2-Methoxyethanol	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub> (109-86-4)	-	Ex	-
	Propan-1-ol (Propyl alcohol)	CH <sub>3</sub> CH <sub>2</sub> CH <sub>2</sub> OH (71-23-8)	-	Ex	-
	Propylene glycol (1,2-Propanediol)	CH <sub>3</sub> CH(OH)CH <sub>2</sub> OH (57-55-6)	-	Ex	-
	Secondary alcohols	R <sub>1</sub> R <sub>2</sub> CHOH	-	Ex	-
Tertiary alcohols	R <sub>1</sub> R <sub>2</sub> R <sub>3</sub> COH	-	Ex	-	
Alkalis	Ammonia	NH <sub>3</sub> (7664-41-7)	10%	Ex	-
	Barium hydroxide	Ba(OH) <sub>2</sub> (17194-00-2)	-	Ex	-
	Calcium hydroxide (lime water)	Ca(OH) <sub>2</sub> (1305-62-0)	-	Ex	-
	Magnesium hydroxide (milk of magnesia)	Mg(OH) <sub>2</sub> (1309-42-8)	-	Ex	-
	Potassium hydroxide (caustic potash)	KOH (1310-58-3)	40%	Ex	-
			20%	Ex	-
10%			Ex	-	
Sodium hydroxide (caustic soda)	NaOH (1310-73-2)	40%	Ex	-	
		20%	Ex	-	
		10%	Ex	-	

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Beverages & Foodstuffs	Beer		-	Ex	-
	Cider		-	Ex	-
	Fermentation liquor		-	Ex	-
	Glucose		-	Ex	-
	Milk		-	M	-
	Sugar liquids		-	Ex	-
	Vinegar		-	M	-
	Whisky and Wine		-	Ex	-
Esters & Ethers	Amyl acetate	CH <sub>3</sub> COO(CH <sub>2</sub> ) <sub>4</sub> CH <sub>3</sub> (628-63-7)	-	Ex	-
	Butyl acetate	C <sub>6</sub> H <sub>12</sub> O <sub>2</sub> (123-86-4)	-	Ex	-
	Dibutyl adipate	[CH <sub>2</sub> CH <sub>2</sub> CO <sub>2</sub> (CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub> ] <sub>2</sub> (105-99-7)	-	Ex	-
	Dibutyl phthalate	C <sub>16</sub> H <sub>22</sub> O <sub>4</sub> (84-74-2)	-	Ex	-
	Dibutyl sebacate	C <sub>18</sub> H <sub>34</sub> O <sub>4</sub> (109-43-3)	-	Ex	-
	Diethyl ether	(C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> O (60-29-7)	-	Ex	-
	Diethyl adipate	C <sub>22</sub> H <sub>42</sub> O <sub>4</sub> (123-79-5)	-	Ex	-
	Diethyl phthalate	C <sub>6</sub> H <sub>4</sub> (C <sub>8</sub> H <sub>17</sub> COO) <sub>2</sub> (117-81-7)	-	Ex	-
	Diethyl sebacate	(CH <sub>2</sub> ) <sub>8</sub> (COOC <sub>8</sub> H <sub>17</sub> ) <sub>2</sub>	-	Ex	-
	Diphenyl isodecyl phosphate	C <sub>22</sub> H <sub>31</sub> O <sub>4</sub> P (29761-21-5)	-	Ex	-
	Ethyl acetate	CH <sub>3</sub> COOCH <sub>2</sub> CH <sub>3</sub> (141-78-6)	-	Ex	-
	Isopropyl ether	C <sub>6</sub> H <sub>14</sub> O (108-20-3)	-	Ex	-
	Methyl acetate	CH <sub>3</sub> COOCH <sub>3</sub> (79-20-9)	-	Ex	-
Halocarbons	Carbon tetrachloride	CCl <sub>4</sub> (56-23-5)	-	G	-
	Chlorobenzene	C <sub>6</sub> H <sub>5</sub> Cl (108-90-7)	-	G	-
	Chloroform	CHCl <sub>3</sub> (67-66-3)	-	G	-
	Dry cleaning fluids		-	G	-
	Methylene chloride (dichloromethane)	CH <sub>2</sub> Cl <sub>2</sub> (75-09-2)	-	P	-
	Perchloroethylene (tetrachloroethylene)	Cl <sub>2</sub> C=CCl <sub>2</sub> (127-18-4)	-	G	-
	1,1,1, - Trichloroethane (methyl chloroform)	CH <sub>3</sub> CCl <sub>3</sub> (71-55-6)	-	G	-

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Hydrocarbons	Aviation fuel (AVCAT, AVGAS, AVTAG, AVTUR)	N/A	-	Ex	-
	Benzene (benzol)	C <sub>6</sub> H <sub>6</sub> (71-43-2)	-	Ex	-
	Cyclohexane	C <sub>6</sub> H <sub>12</sub> (110-82-7)	-	Ex	-
	Gasoline – Ethanol free (Petrol)		-	Ex	-
	Heptane	CH <sub>3</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>3</sub> (142-82-5)	-	Ex	-
	Hexane	CH <sub>3</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>3</sub> (110-54-3)	-	Ex	-
	Iso-octane (2,2,4-trimethylpentane)	(CH <sub>3</sub> ) <sub>3</sub> CCH <sub>2</sub> CH(CH <sub>3</sub> ) <sub>2</sub> (540-84-1)	-	Ex	-
	Kerosene	N/A (8008-20-6)	-	Ex	-
	Paraffin	N/A (8002-74-2)	-	Ex	-
	Pentane	CH <sub>3</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> CH <sub>3</sub> (109-66-0)	-	Ex	-
	Styrene	C <sub>6</sub> H <sub>5</sub> CH=CH <sub>2</sub> (100-42-5)	-	Ex	-
	Toluene (methylbenzene, phenylmethane, toluol)	C <sub>6</sub> H <sub>5</sub> CH <sub>3</sub> (108-88-3)	-	Ex	-
	White Spirit (Stoddard solvent, Mineral spirits)	N/A (8052-41-3)	-	Ex	-
	Xylene (dimethyl benzene, xylol)	C <sub>6</sub> H <sub>4</sub> (CH <sub>3</sub> ) <sub>2</sub> (95-47-6/108-38-3/106-42-3/1330-20-7)	-	Ex	-
Ketones	Acetone	(CH <sub>3</sub> ) <sub>2</sub> CO (67-64-1)	-	Ex	-
	Methyl ethyl ketone (MEK, butanone)	CH <sub>3</sub> C(O)CH <sub>2</sub> CH <sub>3</sub> (78-93-3)	-	Ex	-
Miscellaneous	Bleach (Concentrate)		-	M	-
	Bleach (Dilute cleaning solution)		-	Ex	-
	Brake fluid		-	Ex	-
	Drilling mud		-	Ex	-
	Emulsion paint		-	Ex	-
	Fertilizer solutions		-	Ex	-
	Grease		-	Ex	-
	Ink (water based)		-	Ex	-
	Mercury	Hg	-	Ex	-
	Oil/water mixtures		-	Ex	-
	Water, distilled		-	Ex	-
Water, fresh		-	Ex	-	
Water, sea		-	Ex	-	

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Oils - Mineral	Bunker oils (fuel oils)		-	Ex	-
	Crude oil		-	Ex	-
	Cutting oils, water emulsions		-	Ex	-
	Diesel oil		-	Ex	-
	Lubricating oil		-	Ex	-
	Transformer oil		-	Ex	-
Oils - Vegetable/ Animal	Castor oil		-	Ex	-
	Coconut oil		-	Ex	-
	Cod liver oil		-	Ex	-
	Corn oil		-	Ex	-
	Linseed oil		-	Ex	-
	Olive oil		-	Ex	-
Salts	Aluminium chloride (dry)	AlCl <sub>3</sub> (7446-70-0)	-	Ex	-
	Aluminium sulphate	Al <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> (10043-01-3)	-	Ex	-
	Alums		-	Ex	-
	Ammonium bicarbonate	(NH <sub>4</sub> )HCO <sub>3</sub> (1066-33-7)	-	Ex	-
	Ammonium carbonate	(NH <sub>4</sub> ) <sub>2</sub> CO <sub>3</sub> (506-87-6)	-	Ex	-
	Ammonium chloride	NH <sub>4</sub> Cl (12125-02-9)	-	Ex	-
	Ammonium monophosphate	NH <sub>4</sub> H <sub>2</sub> PO <sub>4</sub> (7722-76-1)	-	Ex	-
	Ammonium phosphate (dibasic)	(NH <sub>4</sub> ) <sub>2</sub> HPO <sub>4</sub> (7783-28-0)	-	Ex	-
	Ammonium phosphate (tribasic)	(NH <sub>4</sub> ) <sub>3</sub> PO <sub>4</sub> (10361-65-6)	-	Ex	-
	Ammonium nitrate	NH <sub>4</sub> NO <sub>3</sub> (6484-52-2)	-	Ex	-
	Ammonium sulfate	(NH <sub>4</sub> ) <sub>2</sub> SO <sub>4</sub> (7783-20-2)	-	Ex	-
	Antimony trichloride	SbCl <sub>3</sub> (10025-91-9)	-	Ex	-
	Barium carbonate	BaCO <sub>3</sub> (513-77-9)	-	Ex	-
	Barium chloride	BaCl <sub>2</sub> (10361-37-2)	-	Ex	-
	Barium sulfate	BaSO <sub>4</sub> (7727-43-7)	-	Ex	-
	Brines		-	Ex	-
	Calcium bisulfite	Ca(HSO <sub>3</sub> ) <sub>2</sub> (13780-03-5)	-	Ex	-
	Calcium carbonate	CaCO <sub>3</sub> (471-34-1)	-	Ex	-
	Calcium chloride	CaCl <sub>2</sub> (10043-52-4)	-	Ex	-
	Calcium hypochlorite	Ca(ClO) <sub>2</sub> (7778-54-3)	-	Ex	-
Calcium sulphate	CaSO <sub>4</sub> (7778-18-9)	-	Ex	-	

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Salts continued	Chromium potassium sulphate (Chrome alum)	KCr(SO <sub>4</sub> ) <sub>2</sub> (10141-00-1)	-	Ex	-
	Copper acetate	Cu(CH <sub>3</sub> COO) <sub>2</sub> (142-71-2)	-	Ex	-
	Copper chloride	CuCl <sub>2</sub> (7447-39-4)	-	Ex	-
	Copper nitrate	Cu(NO <sub>3</sub> ) <sub>2</sub> (3251-23-8)	-	Ex	-
	Copper sulphate	CuSO <sub>4</sub> (7758-98-7)	-	Ex	-
	Ferric chloride (dry)	FeCl <sub>3</sub> (7705-08-0)	-	Ex	-
	Ferric nitrate	Fe(NO <sub>3</sub> ) <sub>3</sub> (10421-48-4)	-	Ex	-
	Ferric sulfate	Fe <sub>2</sub> (SO <sub>4</sub> ) <sub>3</sub> (10028-22-5)	-	Ex	-
	Ferrous chloride	FeCl <sub>2</sub> (7758-94-3)	-	Ex	-
	Ferrous sulfate	FeSO <sub>4</sub> (7720-78-7)	-	Ex	-
	Lead acetate	Pb(CH <sub>3</sub> COO) <sub>2</sub> (301-04-2)	-	Ex	-
	Magnesium bisulfate	Mg(HSO <sub>4</sub> ) <sub>2</sub> (10028-26-9)	-	Ex	-
	Magnesium chloride	MgCl <sub>2</sub> (7786-30-3)	-	Ex	-
	Magnesium sulphate (Epsom salt)	MgSO <sub>4</sub> (7487-88-9)	-	Ex	-
	Mercuric chloride	HgCl <sub>2</sub> (7487-94-7)	-	Ex	-
	Mercuric cyanide	Hg(CN) <sub>2</sub> (592-04-1)	-	Ex	-
	Nickel ammonium sulfate	(NH <sub>4</sub> ) <sub>2</sub> Ni(SO <sub>4</sub> ) <sub>2</sub> (7785-20-8)	-	Ex	-
	Nickel chloride	NiCl <sub>2</sub> (7718-54-9)	-	Ex	-
	Nickel nitrate	Ni(NO <sub>3</sub> ) <sub>2</sub> (13138-45-9)	-	Ex	-
	Nickel sulphate	NiSO <sub>4</sub> (7786-81-4)	-	Ex	-
	Potassium aluminium sulphate (potash alum)	KAl(SO <sub>4</sub> ) <sub>2</sub> (10043-67-1)	-	Ex	-
	Potassium bisulfite	KHSO <sub>3</sub> (7773-03-7)	-	Ex	-
	Potassium bromide	KBr (7758-02-3)	-	Ex	-
	Potassium carbonate	K <sub>2</sub> CO <sub>3</sub> (584-08-7)	-	Ex	-
Potassium chlorate	KClO <sub>3</sub> (3811-04-9)	-	Ex	-	
Potassium chloride	KCl (7447-40-7)	-	Ex	-	
Potassium cyanide	KCN (151-50-8)	-	Ex	-	

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Salts continued	Potassium dichromate	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> (7778-50-9)	-	Ex	-
	Potassium diphosphate	K <sub>2</sub> HPO <sub>4</sub> (7758-11-4)	-	Ex	-
	Potassium ferricyanide	K <sub>3</sub> [Fe(CN) <sub>6</sub> ] (13746-66-2)	-	Ex	-
	Potassium ferrocyanide	K <sub>4</sub> [Fe(CN) <sub>6</sub> ] (13943-58-3)	-	Ex	-
	Potassium iodide	KI (7681-11-0)	-	Ex	-
	Potassium nitrate	KNO <sub>3</sub> (7757-79-1)	-	Ex	-
	Potassium permanganate	KMnO <sub>4</sub> (7722-64-7)	-	Ex	-
	Potassium sulfate	K <sub>2</sub> SO <sub>4</sub> (7778-80-5)	-	Ex	-
	Potassium sulfide	K <sub>2</sub> S (1059-82-5)	-	Ex	-
	Potassium sulphite	K <sub>2</sub> SO <sub>3</sub> (10117-38-1)	-	Ex	-
	Silver nitrate	AgNO <sub>3</sub> (7761-88-8)	-	Ex	-
	Sodium acetate	CH <sub>3</sub> COONa (127-09-3)	-	Ex	-
	Sodium aluminate	NaAlO <sub>2</sub> (1302-42-7)	-	Ex	-
	Sodium bicarbonate	NaHCO <sub>3</sub> (144-55-8)	-	Ex	-
	Sodium bisulfate	NaHSO <sub>4</sub> (7681-38-1)	-	Ex	-
	Sodium bisulfite	NaHSO <sub>3</sub> (7631-90-5)	-	Ex	-
	Sodium borate (borax)	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> (1303-96-4)	-	Ex	-
	Sodium bromide	NaBr (7647-15-6)	-	Ex	-
	Sodium carbonate (soda ash)	Na <sub>2</sub> CO <sub>3</sub> (497-19-8)	-	Ex	-
	Sodium chloride	NaCl (7647-14-5)	-	Ex	-
	Sodium chromate	Na <sub>2</sub> CrO <sub>4</sub> (7775-11-3)	-	Ex	-
	Sodium cyanide	NaCN (143-33-9)	-	Ex	-
	Sodium fluoride	NaF (7681-49-4)	-	Ex	-
	Sodium hypochlorite (bleach)	NaClO (7681-52-9)	-	M	-
	Sodium metaphosphate	(NaPO <sub>3</sub> ) <sub>6</sub> (10124-56-8)	-	Ex	-
	Sodium metasilicate (sodium silicate)	Na <sub>2</sub> SiO <sub>3</sub> (6834-92-0)	-	Ex	-

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

# CHEMICAL RESISTANCE OF BELZONA® 5231

FN 10177



	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Salts continued	Sodium nitrate	NaNO <sub>3</sub> (7631-99-4)	-	Ex	-
	Sodium phosphate (dibasic)	Na <sub>2</sub> HPO <sub>4</sub> (7558-79-4)	-	Ex	-
	Sodium phosphate (tribasic)	Na <sub>3</sub> PO <sub>4</sub> (7601-54-9)	-	Ex	-
	Sodium sulfate	Na <sub>2</sub> SO <sub>4</sub> (7757-82-6)	-	Ex	-
	Sodium sulfide	Na <sub>2</sub> S (1313-82-2)	-	Ex	-
	Stannous chloride (tin chloride)	SnCl <sub>2</sub> (7772-99-8)	-	Ex	-
	Zinc chloride	ZnCl <sub>2</sub> (7646-85-7)	-	Ex	-
	Zinc hydrosulfite	ZnS <sub>2</sub> O <sub>4</sub> (7779-86-4)	-	Ex	-
	Zinc sulfate	ZnSO <sub>4</sub> (7733-02-0)	-	Ex	-

Excellent	Ex	The product is suitable for repeated spillage contact over long periods.
Good	G	The product is suitable for repeated spillage contact over short periods (i.e. with good housekeeping).
Moderate	M	The product is suitable for occasional spillage contact over short periods.
Poor	P	The product is not suitable for any application involving contact with the chemical.
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however, subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose. Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.