

Belzona 9111

FN10114 (Cleaner/Degreaser)



INSTRUCTIONS FOR USE

Degreasing Non-porous Surfaces

a) SMOOTH SURFACES

Wipe thoroughly with a clean rag moistened with **Belzona® 9111**. Change the rag and repeat the process until the rag appears perfectly clean after wiping the surface. Avoid spreading the contamination by cleaning only small areas at a time.

b) ROUGH SURFACES

Brush the **Belzona® 9111** copiously over the surface, using a stiff bristled brush. Continue until the **Belzona® 9111** runs off uncontaminated.

DEGREASING POROUS SURFACES

Note: When oil and grease are deeply impregnated into the substrate, there is no successful method of removing this. The technique below will, however, remove surface oil and grease.

- Mix **Belzona® 9111** with talcum powder or sawdust to form a "sloppy" paste.
- Spread the paste over area to be degreased.
- Leave for 30 minutes and then sweep away.
- Check the surface for cleanliness and if necessary, repeat steps (b) and (c).

CLEANING EQUIPMENT

- Mixing tools, plastic spatulas, applicators and working surfaces should be cleaned immediately after use using a rag soaked in **Belzona® 9111** and then left to dry before re-use (see Drying Times).
- Application tools such as brushes, injection guns, spray units and other equipment should be cleaned using **Belzona® 9121** or other suitable solvents such as methyl ethyl ketone (MEK), acetone or cellulose thinners.

DRYING TIMES

Drying time will vary with the porosity of the substrate and the ambient temperature. The table below gives a guide to the drying time of a thin film of **Belzona® 9111** on a smooth non-porous surface.

| Temperature of Substrate | Drying Time |
|--------------------------|-------------|
| 86°F (30°C) | 35 minutes |
| 68°F (20°C) | 55 minutes |
| 50°F (10°C) | 80 minutes |
| 41°F (5°C) | 100 minutes |

To accelerate drying, the following actions are recommended:-

- Cold surfaces should be warmed before using **Belzona® 9111**.
- Excess **Belzona® 9111** should be removed with a clean cloth or paper towel where possible. This should be carried out by dabbing rather than rubbing the surface, to avoid contamination of the surface by fibres.
- Compressed air should be blown over the treated surface, taking care to ensure that there is an oil filter in the line.

SUITABILITY

There is a possibility of **Belzona® 9111** attacking certain types of plastic and painted surfaces. In cases of doubt, it is strongly recommended that a small portion be tested for solvent attack. If any stickiness is evident after wiping with **Belzona® 9111**, an alternative cleaning agent such as methyl ethyl ketone or white spirit must be used, having once again checked for compatibility.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2012 Belzona International Limited. Belzona® is a registered trademark.

ISO 9001:2008
US3429

Manufactured under an ISO 9000
Registered Quality Management System

